


EMISSION TESTING REPORT

NO REGISTER : 030 / emisi - ply / IX / 2023
 CSO NO : 1161002035
 BUYER : TJIEN FUAT TRADING
 ITEM : HWPW-VC UF (FALCATA)
 QUANTITY / SIZE : 9 pcs / 11,5 mm x 50 mm x 150 mm
 TOTAL PLY : 7
 TYPE OF GLUE : CARB
 DESIKATOR TYPE : ISO 13130
 DESCRIPTION/CONDITIONING OF SAMPLE :
 TESTED FOR :
 TESTING METHOD : JIS A1460 : 2021
 PROD. DATE/SHIFT : 9 September 2023 / 2A
 IN PRECONDITIONING : 11 September 2023
 WEIGHING : 303,82-309,93(0.04%) & 336,72-336,98 (0.08%)
 TEMPERATURE/HUMIDITY : 19,9 °C - 20,2 °C / 66 % - 68 %
 IN CONDITIONING : 14 September 2023 (08,37AM & 08,34 AM)
 TEMPERATURE/HUMIDITY : 19,9 °C - 20,2 °C
 TEST DATE : 15 September 2023 (08,38 AM & 08,35 AM)
 WOOD SPECIES : Falcata

QCL : 1,104 mg/L
 KURVA : $Y = 1,4466 X + 0,0004$
 ASTM D 6007:2014 (ppm) = JIS A 1460:2021 (mg/L)
 22.080

ILLUSTRATION CUT OF SAMPLE



Test Result:

Formaldehyde Emission

Sample Code	Absorbance	Concentration (mg/l)	Corelation to ASTM D 6007:2014 (ppm)		Judgement
R	0.375	0.512	0.538	0.023	PASS
L	0.410	0.564		0.026	
Background :	0.028	0.04 mg/L	Perbedaan dua set sample 10 %		

Butuh, 15 September 2023

Checked by,

 Junaid Basyir
 QC Manager

Tested by,

 Bambang S
 QC Employee

