


**EMISSION TESTING REPORT**

NO REGISTER : 030 / emisi - ply / IX / 2023  
 CSO NO : 1161002035  
 BUYER : TJIEN FUAT TRADING  
 ITEM : HWPW-VC UF ( FALCATA )  
 QUANTITY / SIZE : 9 pcs / 11,5 mm x 50 mm x 150 mm  
 TOTAL PLY : 7  
 TYPE OF GLUE : CARB  
 DESIKATOR TYPE : ISO 13130  
 DESCRIPTION/CONDITIONING OF SAMPLE :  
 TESTED FOR :  
 TESTING METHOD : JIS A1460 : 2021  
 PROD. DATE/SHIFT : 9 September 2023 / 2A  
 IN PRECONDITIONING : 11 September 2023  
 WEIGHING : 303,82-309,93( 0.04% ) & 336,72-336,98 ( 0.08% )  
 TEMPERATURE/HUMIDITY : 19,9 °C - 20,2 °C / 66 % - 68 %  
 IN CONDITIONING : 14 September 2023 ( 08,37AM & 08,34 AM )  
 TEMPERATURE/HUMIDITY : 19,9 °C - 20,2 °C  
 TEST DATE : 15 September 2023 ( 08,38 AM & 08,35 AM )  
 WOOD SPECIES : Falcata

QCL : 1,104 mg/L  
 KURVA :  $Y = 1,4466 X + 0,0004$   
 ASTM D 6007:2014 (ppm) = JIS A 1460:2021 (mg/L)  
 22.080

ILLUSTRATION CUT OF SAMPLE



**Test Result:**

**Formaldehyde Emission**

Sample Code	Absorbance	Concentration (mg/l)	Corelation to ASTM D 6007:2014 (ppm)	Judgement
R	0.375	0.512	0.023 0.024	<b>PASS</b>
L	0.410	0.564		
Background	0.028	0.04 mg/L	Perbedaan dua set sample 10 %	

Butuh, 15 September 2023

Checked by,

Junaid Basyir  
 QC Manager

Tested by,

Bambang S  
 QC Employee

