


EMISSION TESTING REPORT

NO REGISTER : 006 / emisi - ply / IX / 2023
 CSO NO : 1161002035
 BUYER : TJIEN FUAT TRADING
 ITEM : HWPW-VC UF (FALCATA)
 QUANTITY / SIZE : 9 pcs / 14,5 mm x 50 mm x 150 mm
 TOTAL PLY : 7
 TYPE OF GLUE : CARB
 DESIKATOR TYPE : ISO 13130
 DESCRIPTION/CONDITIONING OF SAMPLE :
 TESTED FOR :
 TESTING METHOD : JIS A1460 : 2021
 PROD. DATE/SHIFT : 4 September 2023 / 2A
 IN PRECONDITIONING : 5 September 2023
 WEIGHING : 320,00-320,12(0.04%) & 333,44-333,69 (0.07%)
 TEMPERATURE/HUMIDITY : 19,9 °C - 20,2 °C / 66 % - 68 %
 IN CONDITIONING : 8 September 2023 (08,13AM & 08,10 AM)
 TEMPERATURE/HUMIDITY : 19,9 °C - 20,2 °C
 TEST DATE : 9 September 2023 (08,15 AM & 08,13 AM)
 WOOD SPECIES : Falcata

QCL : 1,104 mg/L
 KURVA : $Y = 1,4466 X + 0,0004$
 ASTM D 6007:2014 (ppm) = JIS A 1460:2021 (mg/L)
 22.080

ILLUSTRATION CUT OF SAMPLE



Test Result:

Formaldehyde Emission

Sample Code	Absorbance	Concentration (mg/l)	Corelation to ASTM D 6007:2014 (ppm)	Judgement
R	0.200	0.243	0.011 0.012	PASS
L	0.217	0.267		
Background	0.025	0.04 mg/L	Perbedaan dua set sample 3 %	

Checked by,

Junaid Basvir
 QC Manager

Butuh, 9 September 2023

Tested by,

Bambang S
 QC Employee

