

EMISSION TESTING REPORT

NO REGISTER : 031 / emisi - ply / IX / 2023
 CSO NO : 1161002035
 BUYER : TJIEN FUAT TRADING
 ITEM : HWPW-VC UF (FALCATA)
 QUANTITY / SIZE : 8 pcs / 17,5 mm x 50 mm x 150 mm
 TOTAL PLY : 9
 TYPE OF GLUE : CARB
 DESIKATOR TYPE : ISO 13130
 DESCRIPTION/CONDITIONING OF SAMPLE :
 TESTED FOR :
 TESTING METHOD : JIS A1460 : 2021
 PROD. DATE/SHIFT : 9 September 2023 / 3B
 IN PRECONDITIONING : 11 September 2023
 WEIGHING : 349,24-349,34(0.03%) & 325,83-325,76 (0.02%)
 TEMPERATURE/HUMIDITY : 19,9 °C - 20,2 °C / 66 % - 68 %
 IN CONDITIONING : 14 September 2023 (08,19 AM & 08,16 AM)
 TEMPERATURE/HUMIDITY : 19,9 °C - 20,2 °C
 TEST DATE : 15 September 2023 (08,20 AM & 08,18 AM)
 WOOD SPECIES : Falcata

QCL : 1,104 mg/L
 KURVA : $Y = 1,4466 X + 0,0004$
 ASTM D 6007:2014 (ppm) = JIS A 1460:2021 (mg/L)
 22.080

ILLUSTRATION CUT OF SAMPLE



Test Result:

Formaldehyde Emission

Sample Code	Absorbance	Concentration (mg/l)		Corelation to ASTM D 6007:2014 (ppm)		Judgement
R	0.274	0.363	0.353	0.016	0.016	PASS
L	0.260	0.342		0.016		
Background	0.028	0.04 mg/L		Perbedaan dua set semple 6 %		

Checked by,

Junaid Basyir
 QC Manager

Butuh, 15 September 2023

Tested by,

Bambang S
 QC Employee

