

Technical Specification

Test	Unit	Average Result		
		3.6mm	12mm	15mm
Thickness	mm	+/- 0.3	+/- 0.4	+/- 0.4
Width	mm	1220		
Length	mm	2440		
Color		White		
Density	g/cm ³	0.6 (+/- 5%)		
Determination of Water Absorbtion	%	<< 1.5		
Shore D Hardness	D type	40 – 47		
Vicat Softening point	° C	70		